

Specjal Plus

TECHNICAL DATA

TECHNICAL DATA	STANDARD	SPECJAL PLUS	SPECJAL PLUS 1.5 MM
CLASSIFICATION			
Classification	EN ISO 10581 EN ISO 10874	Homogeneous single layered vinyl flooring Commercial: 34 / Industrial: 43	Homogeneous single layered vinyl flooring Commercial: 32 / Industrial: 41
CE certification	EN 14041	Yes	Yes
Wear layer binder content	EN ISO 10581	Type II	Type II
TECHNICAL CHARACTERISTICS			
Total thickness	EN ISO 24346	2.0 mm	1.5 mm
Total weight	EN ISO 23997	3300 g/m ²	2400 g/m ²
Wear layer thickness	EN ISO 24340	2.0 mm	1.5 mm
Surface treatment		PUR	PUR
Form of delivery	EN ISO 24341 Sheet (rolls)	23 running metres x 200 cm Art. no. 21097 ___ 3 digit colour number	25 running metres x 200 cm Art. no. 21102 ___ 3 digit colour number
	EN ISO 24342 Tiles (box)	61 x 61 cm - 14 tiles/box = 5.21 m ² Art. no. 21098 ___ 3 digit colour number	-
PERFORMANCES FOR CE MARKING REQUIREMENTS (EN 14041)			
Declaration of Performance	EN 14041	0019-0064-DoP-2019-05	0019-0064-DoP-2019-05
Reaction to fire	EN ISO 13501-1	Bfl-s1	Bfl-s1
	EN ISO 9239-1	≥ 8 kW/m ²	≥ 8 kW/m ²
	EN ISO 11925-2	Pass	Pass
Static electrical discharge	EN 1815	< 2.0 kV	< 2.0 kV
Thermal resistance	EN 12667	Approx. 0.01 m ² K/W	Approx. 0.01 m ² K/W
Slip resistance	EN 13893	μ ≥ 0.3	μ ≥ 0.3
TECHNICAL PERFORMANCES			
Residual indentation	EN ISO 24343-1	Required value: ≤ 0.10 mm Best measured value*: 0.04 mm	Required value: ≤ 0.10 mm Best measured value*: 0.04 mm
Slip resistance	DIN 51130	R9	R9
Castor chair	ISO 4918	Suitable	Suitable
Light fastness	EN ISO 105-B02	≥ level 6	≥ level 6
Dimensional stability	EN ISO 23999	≤ 0.40% for rolls ≤ 0.25% for tiles	≤ 0.40% for rolls -
Flexibility	ISO 24344	Pass	Pass
Chemical resistance	EN ISO 26987	Good resistance	Good resistance
Bacteria resistance	ISO 846 Part C	Does not favour growth	Does not favour growth
Underfloor heating		Suitable - max. 27°C	Suitable - max. 27°C
Seam strength	EN 684	Average value: ≥ 240 N/50mm Individual values: ≥ 180 N/50mm	Average value: ≥ 240 N/50mm Individual values: ≥ 180 N/50mm
ENVIRONMENTAL PERFORMANCES			
Total VOC emissions	ISO 16000-9	≤ 10 μg/m ³ (after 28 days)	≤ 10 μg/m ³ (after 28 days)
COLOURS			
		16	16

The above information is subject to modification for the benefit of further improvement. (08/19). *For information - not binding.
According to the European Regulation N° 305/2011 for CE Marking, the Declarations of Performance are available on our website www.tarkett.com
Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

Customs Tariff: 4820500000



CERTIFIED BY SGS GLOBAL SERVICES

